DuPont[™] Tyvek[®] Housewrap Technical Datasheet



Application: Flexible sheets for water proofing - Part 2: Underlays for walls EN 13859-2: 2010

Style name	1060B			Language	English	
Type of carrier	HDPE			Applicable for	UK, Ireland	
PR	OPERTY	METHOD	UNITS	NOMINAL	MINIMUM	MAXIMUM
	FUNCTIONALITY: WAT	TER VAPOUR TRANSMISSI	ON, WATER TIGHTN	ESS, WEATHER DURA	ABILITY, FIRE CLASS	
Water vapour transmission (sd)		EN ISO 12572 (C)	m	0,01	0,003	0,025
Temperature resistance		-	°C	-	-40	+100
Flexibility at low temperature		EN 1109	°C	-	-	-40
UV exposure		-	months	-	-	4
Product- / Functional layer thickness		-	mm	0,185 / 0,185	-	-
Water tightness		EN 1928 (A)	class	W1	-	-
Water column		EN 20811	m	1,6	-	-
Reaction to fire		EN ISO 11925-2	class	E (*)	-	-
		PHYSICAL AND	MECHANICAL PROP	PERTIES		
Mass per unit area		EN 1849-2	g/m²	61	58,5	63,5
aximum tensile force (MD)		EN 12311-1	N/50mm	310	280	340
Elongation at max. tensile force (MD)		EN 12311-1	%	17,5	15	20
Maximum tensile force (XD)		EN 12311-1	N/50mm	310	270	350
Elongation at max. tensile force (XD)		EN 12311-1	%	20	16	24
Resistance to tearing MD (nail shank)		EN 12310-1	Ν	50	37	65
Resistance to tearing XD (nail shank)	EN 12310-1	Ν	45	32	60
		PROPER	TIES AFTER AGEING	i		
Artificial ageing by UV an	d heat:	EN 1297 & EN 1296	residual value			
Water tightness		EN 1928 (A)	class	W1	-	-
Maximum tensile force (MD)		EN 12311-1	%	80	-	-
MD elongation at max. tensile force		EN 12311-1	%	70	-	-
Maximum tensile force (XD)		EN 12311-1	%	80	-	-
XD elongation at max. t	ensile force	EN 12311-1	%	70	-	-
		ADDITI	ONAL PROPERTIES			
Length (customer related, expressed in m)		EN 1848-2	deviation in %	0	0	-
Vidth (customer related, expressed in mm)		EN 1848-2	deviation in %	0	-0,5	+1,5
Straightness		EN 1848-2	mm/10m	-	-	30
Dimensional stability (MD & XD)		EN 1107-2	%	-	-	1
Resistance to penetration of air		EN 12114	m³/(m² h 50Pa)	-	-	2
Windtight		-	-	yes	-	-

(*): on mineral wool and wood

The product mentioned above, in our opinion, fulfils the criteria of being classified as 'article' (REACH, Art. 3.3). There are no substances intended to be released from this product under normal or reasonably foreseeable conditions of use. The above article to our current knowledge does not contain substances, above the legal threshold, that are on the 'Candidate List' of Substances of Very High Concern (SVHC) as published on the ECHA website.



DuPont de Nemours (Luxembourg) S.à r.l. Rue General Patton, L-2984 Luxembourg DuPont (UK) Limited Unit 29, Hither Green Estate, Clevedon North Somerset, BS21 6XU tyvek.construction@dupont.com

Tel +44 (0) 1275 337660 Fax +44 (0) 1275 879 773

www.building.dupont.co.uk

Effective date: 08/02/2022 First CE: 23/11/2005



Some test methods are modified according to the EN 13959-22010 and/or according to the DuPont ISO 9001/2015 certified quality system (for details please contact your regional DuPont representative). All values are based on roll average. This information corresponds to our current knowledge on the subject. It is offered in accordance with REGULATION (EU) No 305/2011 OF THE EUROPEAN PARLIAMENT AND OF THE COUNCIL of 9 March 2011 laying down harmonised conditions for the marketing of construction products and repealing Council Directive 89/106/EEC. It is not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for any papilcation other than the application as specified herein. This information may be subject to revision as new knowledge and experience becomes available. Since we cannot anticipate all variations in actual end-use conditions, DuPont makes no warranties and assumes no labilities in connection with any use of this information for applications other than the application as specified herein. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right. Product safety information is available on request. This data sheet is a printed document and is valid without signature.